



**GLASS TRANSITION TEMPERATURE
 VERSUS ADDITIVE CONCENTRATION**

With the addition of plasticizers, Aquazol can be softened to a considerable extent. As this figure below shows, the degree of softening (demonstrated by Glass Transition Temperature) can be readily controlled by adjusting both plasticizer concentration and type. For less volatile plasticizers, polyglycols of 400 to 600 molecular weights are preferred.

